

## Sandwich Rubber Sheets

### Technical Specifications

Technical Specification						
Code	Specific Gravity	Hardness (+/- 5)	Tensile Strength	Elongation	Abrasion	Temperature
	Gm/cm3	Shore A	Kg/cm2	%	mm3	°C
<b>STANDARD</b>	<b>ASTM D297</b>	<b>ASTM D2240</b>	<b>ASTM D412</b>	<b>ASTM D412</b>	<b>ASTM D5963</b>	---
<b>SW 64110</b>	1.15	60-40-60	150	500	100	-25 to +70
<b>SW 60110</b>	1.14	60-40-60	150	450	120	-25 to +70