


Corrugated Rubber

A corrugated all-rubber slip resistant matting is specially compounded for use as a floor covering. Backside has a smooth finish. Most widely used where floor protection and safety are vitally important. Applications include general use in industry, home and office. Commonly used in heavy traffic areas. Also used on hard floors, aisles, and behind counters to reduce fatigue. Most widely used where floor protection and safety are important as well as a component to anti-fatigue matting. Use thicker matting for extra heavy duty service. Corrugated rubber matting can also be used as a liner for maintenance and tool carts.



Easily beveled and perforated for entrance or drainage mats. Product strengths include extended wear, all-weather, excellent cleanability and wear resistance. Will not curl, shrink, or separate. Corrugated rubber matting can greatly increase traction and thus aid in prevention of slips and falls while offering greater flexibility.

Finish	Smooth
Powder	No
Color	Black



Technical Specifications

Style#	Hardness (±5)		Tensile Strength		Elongation at break	Abrasion	Compression Set	Temperature Range (General Guidelines)		Oil Swell in ASTM oil 903
	Shore A	PSI	MPa	(min) %	mm ³	(max) %	C°	F°	(max) %	
IR900-70	70	500	3.5	200	-	-	-29°C to +77°C	-20°F to +170°F	-	

Specifications are subject to change without notice

Items Available

Corrugated Rubber					
70 Duro:	1/16"	3/32"	1/8"	3/16"	1/4"

Special Order Item

Sheet Rubber Roll Information

Thickness		Width		Length	
Inches	mm	Inches	Meter	Feet	mm
1/16	1.6	36 & 48	.91 & 1.2	100	30.5
3/32	2.4	36 & 48	.91 & 1.2	75	22.9
1/8	3.2	24, 36 & 48	.61, .91 & 1.2	50	15.3
3/16	4.8	36 & 48	.91 & 1.2	35	10.7
1/4	6.4	24, 36 & 48	.61, .91 & 1.2	35	10.7

- Standard Roll approximate length ± 10%
- Products may vary, please see product listing for specific roll lengths

Typical Physical Properties: The typical physical properties are obtained on ASTM Test slabs and buttons; ASTM and Product Physical Values: ASTM basic requirements for physical properties are based on values obtained from standard laboratory test specimens prepared and tested in accordance with the applicable ASTM test methods. Test results from specimens prepared from finished products may not duplicate values obtained from standard test specimens. Per ASTM D300, Section 7.1, Buyers agrees that when standard test specimens are cut from finished parts in accordance with Practice D3183, a deviation to the extent of 10% on tensile strength and elongation values is permissible. Use of the ASTM Specifications: All of our sheet rubber products are a proprietary blend of polymers formulated to meet designated ASTM D2000 specifications. In our Commercial products, the named polymer is not necessarily the polymer representing the highest percentage of the polymer blend. The various specifications call outs are a valuable guide in selecting the type and grade of sheet rubber for a particular application. In any application, the customer should evaluate the performance requirements and conditions that will affect the working life of the rubber product. Where appropriate, field tests may need to be performed before the style of sheet rubber is selected. If the customer's quality assurance includes the testing of rubber material, the test criteria should specify the physical property call outs of the ASTM specification that is most critical to its application. Polymer type alone may not be adequate for the selecting of the rubber that is best suited for a specific application. Buyer acknowledges the use of its own knowledge, expertise, skill, experience and judgment in the selection of products(s) and /or in the selection, provision, or designation of any specifications or set of specifications for a product(s) agreed upon by the Buyer and Seller. Buyer acknowledges that Seller shall not be liable for, and Buyer assumes all risk of, inaccurate or unsuitable specifications or information provided, selected or designed by the Buyer. RM BILTRITE LLC MAKES NO REPRESENTATIONS OR WARRANTIES WITH RESPECT TO THE SUITABILITY OF MATERIALS FOR A PARTICULAR PURPOSE. BUYERS AND USERS MUST DETERMINE THE SAFETY AND SUITABILITY OF RM BILTRITE'S PRODUCTS FOR THEIR OWN PURPOSES, AND ASSUME ALL RISK, RESPONSIBILITY, AND LIABILITY FOR ALL INJURIES, LOSSES, OR DAMAGES ARISING FROM THE APPLICATION OF THE INFORMATION OR USE OF RM BILTRITE'S PRODUCTS, WHETHER OR NOT CAUSED BY RM BILTRITE'S NEGLIGENCE OR BASED ON STRICT PRODUCT LIABILITY. Terms and conditions are available upon request.